



www.XlntTint.com

Safety/Security Window Film Specifications



	Visible Light Transmission	Exterior Visible Light Reflection	Interior Visible Light Reflection	Solar Heat Gain	Glare Reduction	Ultra Violet	Infrared Light	SPF Rating	Total Solar Energy Rejection	Impact	GSA Level Daylight	GSA Level	GSA Level	GSA Level
				Coefficient (*Shading Coefficient Only)		Light Rejection (UV A/B)	Rejection (2400nm)			Testing (CPSC CFR 1201, Category II)		Wet Glaze (4-Sided)	Metal Attachment (2 Sided)	Metal Attachment (4 Sided)
Huper Ceramic 50 (4-Mil)	50%	10%	10%	0.50	45%	99.9%	68%	>200	50%	N/A	3b	N/A	N/A	N/A
Huper Ceramic 50 (8-Mil)	50%	10%	10%	0.50	45%	99.9%	68%	>200	50%	N/A	3b	2	N/A	N/A
Krystal View Ultra 25 (6-Mil)	27%	35%	20%	*0.31	72%	99%	N/A	N/A	67%	Yes	3b	2	N/A	3a
Commonwealth 4-Mil Clear	86%	10%	N/A	*0.92	N/A	99%	N/A	N/A	20%	Yes	3b	N/A	N/A	N/A
Commonwealth 7-Mil Clear	85%	10%	N/A	*0.91	N/A	99%	N/A	N/A	20%	Yes	3b	2	N/A	3a
Commonwealth 8-Mil Clear	83%	10%	N/A	*0.92	N/A	99%	N/A	N/A	19%	Yes	3b	2	N/A	3a
CP Films 7-Mil Clear	88%	10%	N/A	0.84	2%	99%	N/A	N/A	16%	Yes	3b	2	3b	2
CP Films 8-Mil Clear	88%	10%	N/A	0.82	2%	99%	N/A	N/A	18%	Yes	3b	2	3b	2
BSF 7-Mil Clear	88%	10%	10%	0.82	N/A	99%	N/A	N/A	17%	Yes	3b	N/A	3b	N/A
BSF 8-Mil Clear	89%	10%	10%	0.84	N/A	99%	N/A	N/A	15%	Yes	3b	3a	3b	3a
BSF Silver 20 8-Mil	14%	58%	59%	0.20	N/A	99%	N/A	N/A	79%	Yes	3b	3a	3b	3a
3M Ultra 600	47%	6%	N/A	*0.68	6%	99%	N/A	N/A	N/A	Yes	3b	2	4	3b
3M Ultra 400 NV25	24%	29%	13%	*0.39	72%	99%	N/A	N/A	66%	Yes	N/A	N/A	N/A	N/A
3M 7-Mil Clear	86%	9%	N/A	*0.90	2%	99%	N/A	N/A	4%	Yes	N/A	N/A	N/A	N/A
Clear Glass	88%	8%	8%	0.94			38%		18%					

All specifications taken from published specification sheets from the respected manufacture

©Xlnt Tint 2008

Please refer to individual manufactures Blast reports for details

